




Testrapport:

Våta kuber

CBI Betonginstitutet		VÅTA KUBER					Nominell storlek	
							<input checked="" type="radio"/> 100 mm <input type="radio"/> 150 mm	
Prov	Längd (x)	Bredd (y)	Höjd (z)	Area (A _c)	Massa	Brottlast	Densitet	Tryckhållfasthet
nr	mm	mm	mm	mm ²	g	kN	kg/m ³	f _{c,cube} MPa
A1	104,5	100,0	100,0	10450	2901,2	775	2780	74,1
B1	101,5	100,0	100,0	10150	2793	899	2750	88,6
A2	104,0	100,5	100,0	10400	2852,1	1043	2730	100,3
A3	100,8	100,5	100,0	10000	2850,4	1031	2810	103,1
B2	102,0	100,7	100,0	10271	2794,9	1172	2720	114,1
B3	101,7	100,4	100,0	10170	2804,9	1146	2750	112,7
						medelvärde	98,8	
						standardavvikelse	15,2	