



Testrapport:

Våta kuber

CBI Betonginstitutet your Science partner		VÅTA KUBER				Nominell storlek		
Prov	Längd (x)	Bredd (y)	Höjd (z)	Area (A _c)	Massa	Brottlast	Densitet	Tryckhållfasthet
nr	mm	mm	mm	mm ²	g	kN	kg/m ³	f _{c,cube} MPa
D1	99,8	100,6	100,0	10060	2754	994	2740	98,8
D2	100,3	100,6	100,0	10060	2771	1199	2750	119,1
D3	101,0	101,2	100,4	10120	2764	1288	2690	127,3
				0				
				0				
				0				
						medelvärde		115,1
						standardavvikelse		14,6