



Testrapport:

Våta kuber

CBI Betonginstitutet your Science partner		VÅTA KUBER					Nominell storlek	
Prov	Längd (x)	Bredd (y)	Höjd (z)	Area (A _c)	Massa	Brottlast	Densitet	Tryckhållfasthet
nr	mm	mm	mm	mm ²	g	kN	kg/m ³	f _{c,cube} MPa
F1	101,2	100,6	100,0	10181	2739	1127	2690	110,7
F2	101,5	100,6	100,0	10211	2734	1110	2680	108,7
F3	101,5	100,4	100,0	10150	2743	1084	2690	106,8
				0				
				0				
				0				
						medelvärde		108,8
						standardavvikelse		2,0