



Testrapport:

Våta kuber

CBI Betonginstitutet your Science partner		VÅTA KUBER					Nominell storlek	
Prov	Längd (x)	Bredd (y)	Höjd (z)	Area (A _c)	Massa	Brottlast	Densitet	Tryckhållfasthet
nr	mm	mm	mm	mm ²	g	kN	kg/m ³	f _{c,cube} MPa
G1	102,4	100,8	100,0	10322	2755	961	2670	93,1
G2	105,3	100,2	100,3	10530	2758,3	1239	2610	117,7
G3	103,8	100,0	100,1	10380	2759	1241	2660	119,5
				0				
				0				
				0				
						medelvärde		110,1
						standardavvikelse		14,8