



300 Ponchatoula Pkwy.  
Ponchatoula, LA 70454  
(985) 386-6000  
www.jm-ind.com

## Data Sheet

## JM - SIL 15 - Gray

### Silicone Coated Fiberglass

Base Material	Fiberglass 12.7 oz per Sq Yd
Coating	Gray Silicone 1.2 oz per side
Width	60 in
Total Weight –	15.3 oz/ Sq Yd + 5%
Overall Thickness	17 mils
Tensile Strength	Warp = 414 / Fill = 334 lbs/in ASTM-D-5035
Tear Strength	Warp = 154 / Fill = 157 lbs ASTM-D-5087
Burst Strength	662 lbs. ASTM D- 3786
Abrasion Resistance	Good
Operating Temperature	-65° F to 500°F – continuous 700°F intermediate use Base fabric 1000°F
Flame Resistance	ASTM D- 6413 Afterflame - 0 sec Char Length - .1 inches Afterglow - 2.7 sec

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. Except when in writing, for specific conditions of use, no warrant or guarantee, expressed or implied, is made regarding the performance of any product, since the manner of use and handling are beyond our control. Properties are typical average values and are subject to change.