

Technical Data Sheet

PR5501

High Consistency Silicone Valve & O-ring Lubricant

PREMIERREPAK

Silicone Sealants • Silicone Compounds • Silicone Greases
Anti-Seize Pastes • Aerosol Lubricants • Silicone Fluids
Contract Packaging • Private Label • Turnkey Packaging

FEATURES

- Resistant to a wide range of chemicals; generally resistant to mineral and vegetable oils, air, dilute acids, alkalines, most aqueous solutions and moisture
- Serviceable consistency from -40° to 204°C (-40 to 400°F)
- Practically nonvolatile
- Odorless
- Resistant to a variety of organic and inorganic chemicals
- Excellent rubber lubrication
- Excellent release and sealing properties
- NSF® Registered for Standard 61

COMPOSITION

- Silicone oil
- Inorganic thickener
- Various additives

APPLICATIONS

- Plumbing – all seals
- Lubricant for rubber and plastic O-Rings (Non-silicone)
- Lubricant for water softener and faucet valves
- Mold release where high temperature molds stick to dies and plates.

CERTIFICATION

- *Classified ANSI/NSF Standard 61*
- FDA 21 CFR 178.3570 Lubricants for Incidental Food Contact
- USDA H1 & CNERNA Guide 1992 (France)

HOW TO USE

Can be applied manually to clean, dry substrates using conventional grease application methods, including brush, grease gun, or automatic dispensing.

DESCRIPTION

PR5501 High Consistency Silicone Valve & O-ring Lubricant is designed for the plumbing industry. The primary application is to lubricate the snap ring and O-rings in faucets. It possesses excellent water washout properties that keeps the material in place, and prevents the O-Rings from drying out, cracking and becoming brittle. It is certified and listed NSF for Standard 61, the new requirement for the plumbing industry.

TYPICAL PROPERTIES

The values reported on this sheet should not solely be used for preparing specifications on this product. Please contact PremierRepak, Inc. for assistance in preparing a specification.

Property	Test Method	Typical Value	Range
Color		White to Translucent	
Specific Gravity	CTM	1.03 g/cm ³	
Bleed (200°C /24hrs)	CTM	0.03%	< 2%
Evaporation, (200°C /24hrs)	CTM	0.07%	< 2%
Penetration, mm/10	ASTM D 217	255	200 - 300
Service Temperature Range		-40° to 204°C	

CTM: Corporate Test Method, copies of CTMs are available on request.

STORAGE

PR5501 should be stored at or below 77°F to maintain a maximum shelf life of 60 months from date of manufacture.

LIMITATIONS

PR5501 should not be applied to any surface to be painted or finished. Coatings may not adhere to the silicone-treated surfaces. If contaminated by a silicone coating, parts can be wiped or washed with solvent or detergent. Should not be applied to O-rings or other components made of silicone rubber because they can deteriorate the silicone rubber. Will also slightly swell natural butyl rubbers. Any rubber should be tested for excessive swell or shrink. Not intended for use with liquid oxygen or other strong oxidizing chemicals and should not be used in applications requiring LOX compatibility. This product is not tested, nor approved for medical or pharmaceutical uses.

PACKAGING

PR5501 is available in 5.2oz tubes (150g); 14.1oz grease cartridges (400g); 1gallon pails (3.6kg); 5 gallon pails (18.1kg) and 55 gallon drums (180kg).

Special packaging and private labeling is available upon request.



PREMIERREPAK
Innovative Ideas...Moving You Forward

8351 185th Street • Tinley Park, IL 60487 • Ph: 855.737.2500 • Fx: 708.429.4280
www.premierrepak.com • customerservice@premierrepak.com